



Ficha Técnica

Product Data Sheet

Porcelanato
Glazed Porcelain
ANEXO G
ANNEX G
Grupo BIA
Group BIA


FLIRT

Código Code: GD-1937
Fecha Date: 2019-02-11
Revisión Review: 1

NOMBRE NAME	CODIGO CODE	ACABADO FINISH	ESPESOR mm THICKNESS mm	DIMENSION DE FABRICACION mm MANUFACTURING DIMENSION mm
FLIRT	70EN1660E	NATURAL	7.8	323 X 323

N°	CARACTERÍSTICA CHARACTERISTIC	ENSAYO TEST	NORMA / NORM NTE INEN - ISO 13006	GRAIMAN
1	Longitud y ancho Length and width	10545-2	(± 0,6%), ± 2,0 mm	(± 0,5%) ± 1,5 mm
2	Espesor Thickness		(± 5%), ± 0,5 mm	± 0,5 mm
3	Rectitud de los lados Straightness of sides		(± 0,5 %), ± 1,5 mm	(± 0,5 %), ± 1,5 mm
4	Rectangularidad Rectangularity		(± 0,5 %), ± 2,0 mm	(± 0,5 %), ± 1,5 mm
5	Curvatura de centro Central curvature		(± 0,5 %), ± 2,0 mm	(± 0,4 %), ± 1,5 mm
6	Curvatura de borde Side curvature		(± 0,5 %), ± 2,0 mm	(± 0,5 %), ± 2,0 mm
7	Alabeo Warpage		(± 0,5 %), ± 2,0 mm	(± 0,4 %), ± 1,5 mm
8	Calidad de la superficie Surface quality		Mínimo 95% libre de defectos visibles Minimum 95% free of visible defects	Mínimo 95% libre de defectos visibles Minimum 95% free of visible defects
9	Absorción de agua Water absorption	10545-3	E _b ≤ 0.5 %, Máximo individual 0.6 % E _b ≤ 0.5%, Individual maximum 0.6%	E _b ≤ 0.5 %, Máximo individual 0.6 % E _b ≤ 0.5%, Individual maximum 0.6%
10	Resistencia a la rotura Resistance to breakage	10545-4	a) Espesor ≥ 7.5 mm No menor que 1300 Newton A) Thickness ≥ 7.5 mm Not less than 1300 Newton b) Espesor < 7.5 mm No menor que 700 Newton B) Thickness <7.5 mm Not less than 700 Newton	a) Espesor ≥ 7.5 mm No menor que 1300 Newton A) Thickness ≥ 7.5 mm Not less than 1300 Newton b) Espesor < 7.5 mm No menor que 700 Newton B) Thickness <7.5 mm Not less than 700 Newton
11	Módulo de rotura Modulus of rupture		Mínimo 35 Minimum 35 Mínimo individual 32 Minimum individual 32	Mínimo 35 Minimum 35 Mínimo individual 32 Minimum individual 32
12	Resistencia a la Abrasión Superficial PEI Resistance to surface abrasion PEI	10545-7	Reportar la clase de abrasión y los ciclos aprobados FICHA TÉCNICA Report the type of abrasion and the approved cycles TECHNICAL DATA SHEET	3
13	Resistencia a la Abrasión Profunda, Baldosas No Esmaltadas Resistance to Deep Abrasion, Unglazed Tiles	10545-6	No Aplica Not apply	No Aplica Not apply
14	Resistencia al cuarteado Crazing resistance	10545-11	Requerida Required	No presenta Cuarteo Does not present Quartz
15	Resistencia a las manchas Stain Resistance	10545-14	Mínimo CLASE 3 Minimum Class 3	Mínimo CLASE 4 Minimum CLASS 4
16	Resistencia a los agentes químicos Resistance to chemical agents	10545-13	Resistencia a los agentes químicos caseros y sales de piscina Mínimo GB Resistance to household chemicals and pool salts Minimum GB	GB
			Resistencia a los ácidos y álcalis de baja concentración. El fabricante declara la clasificación. Resistance to acids and alkalis of low concentration. The manufacturer declares the classification.	GLB
			Resistencia a ácidos y álcalis de alta concentración MÉTODO DE ENSAYO DISPONIBLE Resistance to acids and alkalis of high concentration. TEST METHOD AVAILABLE	GHB
17	Dureza Mohs Scratch hardness (Mohs)	UNE-EN 15771	No Aplica Not apply	5
18	Coefficiente de Fricción DCOF (húmedo) Coefficient of Friction DCOF (wet)	ANSI A 137.1	≥ 0.42	0.51

<p>CATEGORÍAS DE V-RATING: En todo producto de cerámica, como característica inherente existen variaciones de color, tono y textura. Existen cuatro indicadores asignado para informar a los consumidores, el grado de variación que se puede ver presentar entre las piezas de una caja de determinado producto.</p> <p>CATEGORIES OF V-RATING: In every ceramic product, as inherent characteristic there are variations of color, tone and texture. There are four indicators assigned to inform consumers, the degree of variation that can be seen to present between the pieces of a product box.</p>	V1	<p>Variación mínima de color, tono y textura entre las piezas de una caja del producto. Luego de la instalación en producto ofrece una apariencia uniforme.</p> <p>Minimum variation of color, shade and texture between the pieces of a product box. After installation of the product it offers a uniform appearance.</p>
<p>RECOMENDACIÓN DE USO: viene definida por la combinación del PEI y MOHS</p> <p>RECOMMENDATION FOR USE: is defined by the combination of PEI and MOHS</p>	RG	<p>Residencial General: Son baldosas cerámicas esmaltadas, para instalar en ambientes protegidos de agentes abrasivos (arena, gravilla, etc). Recomendada para todas las áreas residenciales privadas, incluidas cocinas y terrazas. Además para habitaciones de hoteles, con sus respectivos servicios, cuartos de hospitales, etc.</p> <p>General Residential: They are glazed ceramic tiles, to be installed in environments protected from abrasive agents (sand, gravel, etc.). Recommended for all private residential areas, including kitchens and terraces, in addition to hotel rooms with their respective services, hospital rooms, etc.</p>



Certificaciones del Sistema



Certificación al Producto

